

NYLON-LIKE WEBBING

Combining the benefits of Nylon and PET for a yarn in a class of its own

WEBBING SLING

Widths available
 Thickness (mm)
 Elongation at 9,900 lbs
 Tensile
 Tensile % retention after abrasion
 (2,500 cycles Hex-Bar Abrasion)
 Crocking wet
 Crocking dry
 *Xenon at 225.6 kj

1,2,3,4 and 6 inches
 4.0 - 4.5 mm
 10% - 15%
 9,800 lbs/in
 +/- 50%
 3.4 min
 3.4 min
 DE: 9.41

*UV resistance 9x superior compared to the industry's average

CHEMICAL RESISTANCE

| | Strength (kgf) | Elongation (%) | Retention rate of Strength (%) |
|--|----------------|----------------|--------------------------------|
| Before | 15.50 | 10.2 | |
| After 6 hours immersion in a 3.5 pH solution | 15.52 | 9.9 | 100 |
| Before | 15.26 | 10.1 | |
| After 6 hours immersion in a 13 pH solution | 15.39 | 10.4 | 100 |

Electric Green
 Printing & Cutting Available

A polyester yarn that offers superior webbing performance

Behaves like Nylon and even better

More economic compared to Nylon webbing

Strongly recommend the use of Nylon-Like sewing thread for sling assembly in order to meet the WLL and chemical resistance

Benefits from Nylon 6

- High elongation
- High tenacity
- Durability
- Resistant to alkalis

Benefits from PET

- Low moisture regain
- Low stiffness
- Heat Resistant
- Resistant to acids
- Excellent UV resistance
- Lower shrinkage than Nylon

A product of



Belt-Tech

Belt-Tech USA Inc.

Contact Info: Della Picken
 1-877-932-6455 Ext. 308
 www.belt-tech.com